

Applications of Photocatalytic Disinfection

[Joanne Gamage](#) and [Zisheng Zhang](#)

Department of Chemical and Biological Engineering, University of Ottawa,
161 Louis Pasteur, Ottawa, ON, K1N6N5, Canada

Received 28 June 2010; Accepted 11 August 2010

Academic Editor: Detlef W. Bahnemann

Copyright © 2010 Joanne Gamage and Zisheng Zhang. This is an open access article distributed under the [Creative Commons Attribution License](#), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Abstract

Due to the superior ability of photocatalysis to inactivate a wide range of harmful microorganisms, it is being examined as a viable alternative to traditional disinfection methods such as chlorination, which can produce harmful byproducts. Photocatalysis is a versatile and effective process that can be adapted for use in many applications for disinfection in both air and water matrices. Additionally, photocatalytic surfaces are being developed and tested for use in the context of “self-disinfecting” materials. Studies on the photocatalytic technique for disinfection demonstrate this process to have potential for widespread applications in indoor air and environmental health, biological, and medical applications, laboratory and hospital applications, pharmaceutical and food industry, plant protection applications, wastewater and effluents treatment, and drinking water disinfection. Studies on photocatalytic disinfection using a variety of techniques and test organisms are reviewed, with an emphasis on the end-use application of developed technologies and methods.

1. Introduction

Applications of photocatalytic processes are widely recognized as viable solutions to environmental problems [1–3]. Disinfection of bacteria is of particular importance, because traditional methods such as chlorination are chemical intensive and have many associated disadvantages. For example, in

water treatment applications, chlorine used for disinfection can react with organic material to generate chloro-organic compounds that are highly carcinogenic [4, 5]. Furthermore, some pathogens such as viruses, certain bacteria such as *Legionella*, and protozoans such as *Cryptosporidium* and *Giardia lamblia* cysts have been known to be resistant to chlorine disinfection [6, 7]. Other treatment alternatives such as ozonation and irradiation using germicidal lamps (254 nm) have their own problems and limitations, such as the lack of residual effect [8] and generation of small colony variants [9] for the latter and production of toxic disinfection byproducts for the former [10].

In comparison, the semiconductor commonly used in photocatalytic processes is nontoxic, chemically stable, available at a reasonable cost, and capable of repeated use without substantial loss of catalytic ability [11]. Heterogeneous photocatalysis using titanium dioxide is a safe, nonhazardous, and ecofriendly process which does not produce any harmful byproducts. Extensive research in this field has been done in the area of photocatalytic removal of organic, inorganic, and microbial pollutants [12, 13].

The mechanism of bactericidal action of photocatalysis, as reported by Sunada et al. is attributed to the combination of cell membrane damage and further oxidative attack of internal cellular components, ultimately resulting in cell death [14].

Since the breakthrough work of Matsunaga et al. in 1985 reporting the application of photocatalysis for the destruction of *Lactobacillus acidophilus*, *Saccharomyces cerevisiae*, and *Escherichia coli* using platinum-loaded [15], there has been much interest in the biological applications of this process. A very comprehensive review of the application of photocatalysis for disinfection of water is given by McCullagh et al. [16], with many others available in the literature [17–21].

Research in the field of photocatalytic disinfection has been very diverse, with the /UV process being shown to successfully inactivate many microorganisms including bacteria such as *E. coli* [22–24], *L. acidophilus* [15], *Serratia domonas stutzeri* [25], *Bacillus pumilus* [26], *Streptococcus mutans* [1], yeasts such as *S. cerevisiae* [15], algae such as *Chlorella vulgaris* [15], and viruses such as phage MS2 [15, 27, 28], *B. fragilis* bacteriophage [15, 27], Poliovirus I [28], *Cryptosporidium parvum* [29], and *Giardia intestinalis* [30].

Research efforts are being made to improve the efficiency of the catalyst by means of doping with various metals [31–33] and nonmetals [34, 35]. Other parameters which can be varied in a photocatalytic process, such as the source of ultraviolet irradiation [18] and factors affecting process efficiency [36] have also been under investigation. Additionally, there are countless reactor designs and configurations [37, 38] used to exploit photocatalytic disinfection for a wide range of applications, as this process can be used in both water and air matrices [39]. The current review will focus on developments in photocatalytic disinfection for application in the following contexts: indoor air and environmental health, biological and medical applications, laboratory and hospital applications, pharmaceutical and food industry, plant protection

applications, wastewater and effluents treatment, and finally, drinking water disinfection.

2. Indoor Air and Environmental Health

The photocatalytic process is well recognized for the removal of organic pollutants in the gaseous phase such as volatile organic compounds (VOCs), having great potential applications to contaminant control in indoor environments such as residences, office buildings, factories, aircrafts, and spacecrafts [40, 41].

To increase the scope of the photocatalytic process in application to indoor air, the disinfection capabilities of this technique are under investigation [39]. Disinfection is of importance in indoor air applications because of the risk of exposure to harmful airborne contaminants. Bioaerosols are a major contributor to indoor air pollution, and more than 60 bacteria, viruses, and fungi are documented as infectious airborne pathogens. Diseases transmitted via bioaerosols include tuberculosis, Legionnaires, influenza, colds, mumps, measles, rubella, small pox, aspergillosis, pneumonia, meningitis, diphtheria, and scarlet fever [42]. Traditional technologies to clean indoor air include the use of activated charcoal filters, HEPA filters, ozonation, air ionization, and bioguard filters. None of these technologies is completely effective [20].

In the pioneering work by Goswami et al. [43, 44] investigating the disinfection of indoor air by photocatalysis, a recirculating duct facility was developed to inactivate biological contaminants in air with photocatalytic techniques. Experiments using *Serratia Marcescens* in air achieved a 100% destruction of microorganisms in a recirculating loop in 600 minutes [43]. This time was reduced to less than 3 minutes in later experiments [45].

Photocatalytic oxidation can also inactivate infectious microorganisms which can be airborne bioterrorism weapons, such as *Bacillus anthracis* (Anthrax) [46–48]. A photocatalytic system was investigated by Knight in 2003 to reduce the spread of severe acute respiratory syndrome (SARS) on flights [49], following the outbreak of the disease. Similarly, in 2007 the avian influenza virus A/H5N2 was shown to be inactivated from the gaseous phase using a photocatalytic prototype system [39].

Inactivation of various gram-positive and gram-negative bacteria using visible light and a doped catalyst [50] and fluorescent light irradiation similar to that used in indoor environments was studied [51] and shows great promise for widespread applications.

It was also shown that *E. coli* could be completely mineralized on a coated surface in air [42]. Carbon mass balance and kinetic data for complete oxidation of *E. coli*, *A. niger*, *Micrococcus luteus*, and *B. subtilis* cells and spores were subsequently presented [52]. A comprehensive mechanism and detailed description of the photokilling of *E. coli* on coated surfaces in air has been extensively studied in order to understand to a considerable degree and in a quantitative way the kinetics of *E. coli* immobilization and abatement using

photocatalysis, using FTIR, AFM, and CFU as a function of time and peroxidation of the membrane cell walls [53–57].

Novel photoreactors and photo-assisted catalytic systems for air disinfection applications such as those using polyester supports for the catalyst [58], carbon nanotubes [59], combination with other disinfection systems [60], membrane systems [61], use of silver bactericidal agents in cotton textiles [62–64] for the abatement of *E. coli* in air, high surface area CuO catalysts [65], and structure silica surfaces [66] have also been reported.

In terms of environmental health, the antifungal capability of photocatalysis against mold fungi on coated wood boards used in buildings was confirmed [67] using *A. niger* as a test microbe, and UVA irradiation.

3. Biological and Medical Applications

Due to the disinfection abilities of photocatalytic processes, they are being explored for use in medical applications. Studies have been done using coatings on bioimplants to implement photocatalysis for antibacterial purposes [47, 68, 69]. Shiraishi et al. explored the photocatalytic activity of *S. aureus*, a common pathogenic bacterium in implant-related infection, using film on stainless steel and titanium substrates [70]. The bactericidal effect of the coating was confirmed upon UV irradiation, and the use of these coated photocatalytic substrates present a useful strategy for the control of such infections associated with biomedical implants.

Photocatalysis is also able to kill animal cells, such as in the antitumor activity shown using subcutaneous titania injection onto skin tumours followed by 40 minutes of UV illumination [71]. This procedure produced a tenfold tumour volume reduction after three weeks, where the catalyst and light alone control runs showed tumor increases in volume by factors of 30–50. The use of photocatalysis for cancer cell treatment has also been documented elsewhere [1, 72].

As previously alluded to in air-disinfection strategies, photocatalysis can be employed to remove harmful airborne biological threats such as Anthrax [48, 73]. In this sense, it can be an effective technique for combating bioterror and preventing the spread of airborne biological threats.

4. Laboratory and Hospital Applications

Particularly in microbiological laboratories and in areas in intensive medical use, frequent and thorough disinfection of surfaces is needed in order to reduce the concentration of bacteria and to prevent bacterial transmission. Conventional methods of disinfection with wiping are not long-term effective, and are staff and time intensive. These methods also involve the use of harsh and aggressive chemicals. Disinfection with hard ultraviolet light (UVC) is usually unsatisfactory, since the depth of penetration is inadequate and there are occupational health risks [74].

Photocatalytic oxidation on surfaces coated with titanium dioxide offers an alternative to traditional methods of surface disinfection. Research has examined the biocidal activity of thin films of titania anchored to solid surfaces [74–76]. The effectiveness of this process was demonstrated using bacteria relevant to hygiene such as *E. coli*, *P. aeruginosa*, *S. aureus*, and *E. faecium* [74]. The inactivation of *E. coli* (ATCC8739) cells deposited on membrane filters during irradiation with fluorescent light was also shown as an application of self-disinfecting surfaces [77].

Thin films deposited on stainless steel using a novel flame-assisted CVD technique were also tested for antimicrobial activity on *E. coli* [69]. There is a wider range of applications for this self-disinfecting material because of the desirable mechanical properties and resistance to corrosion of stainless steel. Transparent films on this substrate have also been shown to be effective for sterilization of *B. pumilus* [78]. In this study, the -coated stainless steel was shown to have a higher photocatalytic activity than the same coating on glass substrates.

Titania photocatalysts doped with CuO were coated on surfaces and evaluated for biocidal activity [79]. This investigation also explored the synergistic effect of photocatalysis and toxicity of copper to inactivate bacteriophage T4 and *E. coli*.

Enhanced photocatalysis using nitrogen-doped was also reported for its visible light-induced bactericidal activity against human pathogens [80]. It was proposed in this study that photocatalytic disinfection using visible light can offer a means of continuous disinfection for surfaces constantly in contact with humans, such as door handles and push buttons. Visible light-induced inactivation of *E. coli* was also studied using titania codoped with nitrogen and sulfur [81–84]. This introduces new disinfectant opportunities in public environments, such as public toilets, schools, hospitals, stations, airports, hotels, or public transportation, which are ideal places for the transmission of pathogens [85, 86].

Photocatalysis has also been investigated for the inactivation of prions, the infectious agents of a family of transmissible, fatal, neurodegenerative disorders affecting both humans and animals [87]. These prions may be transmitted via ingestion of contaminated food or during medical treatments with contaminated biological materials or surgical tools. The effectiveness of photocatalytic oxidation for inactivating these prions can help to reduce the risk of spread and demonstrates the practical applications of this technology for disinfection of contaminated surfaces and inanimate objects.

Another application of photocatalysis in a hospital setting is for the control of Legionnaire's disease, which is associated to hot water distribution systems containing bacteria of the *Legionella* species [88]. In laboratory scale studies, it was shown that photocatalytic oxidation using /UV was able to mineralize the cells of four strains of *L. pneumophila* serogroup 1 (strain 977, strain 1009, strain 1004, and ATCC 33153) upon prolonged treatment. This implies that the process used might be a viable alternative to the traditional disinfection

processes used for the control of *Legionella* bacteria in hospital hot water systems, such as thermal eradication and hyperchlorination [89].

5. Pharmaceutical and Food Industry

Due to the antibacterial applications of TiO_2 -mediated photooxidation, this process shows promise for the elimination of microorganisms in areas where the use of chemical cleaning agents or biocides is ineffective or is restricted by regulations, for example in the pharmaceutical and food industries [33]. TiO_2 is nontoxic and has been approved by the American Food and Drug Administration for use in human food, drugs, cosmetics, and food contact materials [90].

TiO_2 powder-coated packaging film was shown to inactivate *E. coli* (ATCC 11775) in vitro when irradiated with UVA light [90]. Actual tests on cut lettuce stored in a TiO_2 -coated film bag under such irradiation also showed this method to be effective for the reduction of *E. coli* colonies, indicating that the coated film could reduce microbial contamination on the surfaces of solid food products and hence reduce the risk of microbial growth in food packaging. Photocatalysis has also shown to be effective for the inactivation of other foodborne bacteria such as *Salmonella choleraesuis* subsp., *Vibrio parahaemolyticus*, and *Listeria monocytogenes* [69].

Surface disinfection is also of importance to food processing, as foodborne infections can be caused by the proliferation and resistance to cleaning procedures of pathogenic germs on surfaces of the production equipment in such industries. Studies with *E. coli* strains (PHL 1273) [91] synthesizing curli, a type of appendage that allows the bacteria to stick to surfaces and form biofilms, were able to inactivate this organism using titania and various types of UV irradiation. In dark events studies, following the bacterial inactivation, no bacterial cultivability was recovered after 48 hours, indicating that the durability of the disinfection was adequate. Nitrogen doping of the titania photocatalyst was also reported in a separate study [92] with the use of visible light to inactivate *E. coli* and biofilm bacteria. Disinfection of *E. coli* using TiO_2 -containing paper and UV fluorescent irradiation has also been shown [93].

6. Plant Protection Applications

Photocatalytic disinfection is potentially very important in the control and inactivation of pathogenic species present in the nutritive solution in circulating hydroponic agricultures [94]. Many plant pathogens can be transmitted by irrigation and recycled waters used in hydroponic agriculture. Conventional bactericidal methods often apply chemical pesticides to disinfect these pathogens, but these are often harmful to animals, humans, and the environment due to their residual toxicity [95]. Photocatalytic disinfection of these plant pathogens using TiO_2 may be used as a new tool for plant protection and an alternative to the use of harsh chemicals.

Using thin film on a glass substrate and UVA irradiation, *Enterobacter cloacae* SM1 and *Erwinia carotovora* subsp. *Caratovora* ZL1, phytopathogenic enterobacteria that cause basal rot and soft rot in a variety of vegetable crops, were efficiently inactivated [95]. Subsequent studies investigated the effects of doping the titania catalyst with various photosensitive dyes using visible light irradiation [96]. It was shown that the disinfection of the phytopathogenic bacteria causing basal and soft rot could be efficiently carried out under visible light using these doped catalysts.

Solar photocatalytic disinfection using batch process reactors and titania photocatalysts was also shown to be effective for the disinfection of five wild strains of the *Fusarium* genus (*F. equiseti*, *F. oxysporum*, *F. anthophilum*, *F. verticilloides*, and *F. solani*), a common plant pathogen [97]. In this case, natural solar radiation was used and the photocatalytic solar disinfection was compared to solar-only disinfection for these fungi. The photocatalytic process was found to be faster than the solar-only disinfection in all trials.

The disinfecting ability of titania photocatalyst films was also tested on pathogens of mushroom diseases: *Trichoderma harzianum*, *Cladobotryum varium*, *Spicellum roseum*, and *P. tolaasii*. The disinfection of these species was confirmed by experiments conducted in mushroom growing rooms under black light irradiation, and subsequently, white light irradiation [98].

7. Wastewater and Effluents

The use of photocatalysis for water and wastewater treatment is a topic well documented in the literature, especially with respect to solar photocatalysis [17–21, 99–102]. Due to the ability of photocatalysis to mineralize many organic pollutants, it has been used for remediation of contaminated groundwaters through the use of parabolic solar concentrating type reactors. Photocatalysis has been used in engineering scale for solar photocatalytic treatment of industrial nonbiodegradable persistent chlorinated water contaminants [21], and in field scale for treatment of effluents from a resins factory [103]. This process has also shown to be effective for treatment of wastewaters from a 5-fluororacil (a cancer drug) manufacturing plant [104], distillery wastewater [105], pulp and paper mill wastewater [106], dyehouse wastewater [17], and oilfield produced water [35].

However, the disinfection capabilities of photocatalytic processes have not thoroughly been exploited for treatment of wastewaters. Wastewater reclamation and reuse is of growing importance, especially in areas where the freshwater supply is limited, and so effective disinfection of wastewaters is necessary. Any technical means of sewage reuse is limited by persistent organic pollutants and microorganisms which are not removed by the conventional mechanical and biological treatment train [107]. Additional treatment is therefore necessary before any reuse can take place.

Early work on photocatalytic disinfection of municipal secondary wastewater effluents showed an inactivation of coliform bacteria and Poliovirus I using

suspensions of titanium dioxide and fluorescent and sunlight irradiation, respectively [28].

Photocatalysis is also useful for disinfection of sewage containing organisms which are highly resistant to traditional disinfection methods, such as *Cryptosporidium parvum* [108] and noroviruses [109].

Municipal wastewater effluents from a sewage disposal plant in Hannover, Germany were treated in a slurry reactor under UVA irradiation to simultaneously detoxify and disinfect the samples [110]. The photocatalytic treatment was able to diminish the concentration of dissolved organic pollutants (indicated by TOC and COD), and as well inactivate pathogenic microorganisms (indicated by *E. coli*). A similar result was obtained from studies monitoring Faecal streptococci and total coliforms using slurry systems with UVA lamps and solar irradiation, respectively [111].

The investigation of bacterial consortia of *E. coli* and *Enterococcus* species present in real wastewaters from a biological wastewater treatment plant in Lausanne (Switzerland) [112] indicated that the *Enterococcus* species are less sensitive to photocatalytic treatment than coliforms and other gram-negative bacteria. Additionally, the effects of temperature, turbidity, and various other physical parameters of the samples on the photocatalytic inactivation of *E. coli* were investigated [113].

Further research investigates enhanced photocatalysis to improve the efficiency of disinfection of wastewaters for reuse, for example, by the use of titania-activated carbon catalyst mixtures [114], and through the development of nanocrystalline photocatalytic membranes [115]. The latter is of particular importance in aeronautical applications, as it combines membrane separation technologies with advanced oxidation technologies to create photocatalytic composite membranes designed for the treatment and reuse of water on long-duration space missions [116].

An inexpensive approach to synthesizing a novel nitrogen-doped photocatalyst has also been developed [117], improving the efficiency of visible light-induced disinfection of wastewaters, and introducing a new generation of catalysts for this application.

8. Drinking Water Disinfection

Titania photocatalysis has been proven to be effective in the removal of chemical compounds and microbiological pathogens from water. A thorough review by McCullagh et al. [16] of the application of photocatalysis for the removal of biological species in this context examines studies on the disinfection effect of suspensions, effect of additives and pH, respectively, on the photocatalytic abilities and disinfection effect of thin films, and the effect of electrochemically applied potential on the photobactericidal effect of thin films. The current discussion will focus on the various applications of photocatalytic drinking water disinfection.

8.1. Drinking Water Production in Developing Countries

In 2004, it was estimated that about 15% of the world's population, mostly living in the less-favored regions of the planet, did not have access to enough fresh water to satisfy their daily needs, and this number was expected to double by 2015 [118]. This represents a serious public health issue since waterborne, water-washed, and water-based diseases are associated with lack of improvement in domestic water supply and adequate sanitation [119]. Development of low cost-effective methods for removal of pollutants from water supplies can help alleviate this problem. Especially in rural communities, water disinfection must have sufficiently low operational costs. Alternative technologies to traditional chlorination are now being considered for household use [120].

Solar disinfection (SODIS) is a simple technology that is capable of inactivating many waterborne pathogenic bacteria using the combined effect of solar UVA radiation and temperature [121–124]. This method is low cost and does not produce toxic byproducts, however, limits the volume of water subject to treatment (typically 2L per exposed water bottle) and has a disadvantageous long time of process (typically 2 day exposure for complete inactivation) [119]. The combination of sunlight and photocatalyst is a promising option for water treatment in areas with insufficient infrastructure but high yearly sunshine. The use of compound parabolic reactors as an efficient technology to collect and focus diffuse and direct solar radiation onto a transparent pipe containing contaminated water has demonstrated feasibility to disinfect water using suspensions [125–127].

The European Union International Cooperation program (INCO) has sponsored initiatives for developing a solar photocatalysis-based cost-effective technology for water decontamination and disinfection in rural areas of developing countries, the SOLWATER and AQUACAT projects, respectively [94]. These projects are aimed at developing a solar reactor to decontaminate and disinfect small volumes of water, and field tests with the final prototypes were carried out to validate operation under real conditions [127].

The final SOLWATER prototype was composed of two tubes containing Alstrohm paper impregnated with titanium dioxide, and two tubes containing a supported photosensitizer [94]. These tubes are placed on a compound parabolic concentrating collector and run in series, where the electricity is provided by a solar panel (Figure 1).

Field tests using the SOLWATER prototype placed the reactor in the yard of a shanty house in Los Pereya, Tucuman, Argentina and studied the removal of bacterial contamination during three months of testing using natural water contaminated with coliforms, *E. Faecalis*, and *P. aeruginosa*, as well as high levels of natural organic matter and variable inorganic pollutants [127]. The SOLWATER reactor was shown to be effective for this application. Similar tests have been performed in photoreactors installed in various geographic regions, including Egypt, France, Greece, Mexico, Morocco, Peru, Spain, Switzerland, and Tunisia [94].

Other research in the field of potable water production in developing countries includes the development of affordable and efficient technology in the form of

batch borosilicate glass and PET plastic SODIS reactors fitted with flexible plastic inserts coated with powder [128]. These were shown to be 20 and 25% more effective, respectively, than SODIS alone for the inactivation of *E. coli* K12. This novel system was also able to reduce the concentration of *Cryptosporidium parvum* oocysts present [129]. It should be also noted that there has also been significant research done in the advance of solar disinfection of this highly resistant organism using SODIS alone [123, 130, 131].

8.2. Surface Water Treatment

While the majority of photocatalytic disinfection studies reported are carried out with distilled water or buffer solutions [16], there have been attempts to quantify the effects of the chemical constituents of natural surface waters on photocatalysis [132, 133]. It has been shown, using surface water samples, that the presence of inorganic ions and humic acids decrease the photocatalytic disinfection rate of *E. coli* [133].

Other efforts have been made to evaluate photocatalysis applications using real waters [134–138]. For example, the integration of photocatalysis into traditional water treatment processes for the removal of organic matter, which has variable levels during the year, was studied in the UK using three surface water samples [136].

Natural water samples from the Cauca River in Cali, Columbia showed drastic *E. coli* culturable cell concentration increase 24 hours after stopping irradiation [135]. This was not observed for the control experiment using an *E. coli* suspension in distilled water. It was concluded that caution should be taken when making predictions based on simple models as they are not necessarily representative of natural crude water samples.

The effect of pH, inorganic ions, organic matter, and on *E. coli* photocatalytic inactivation by was studied by simulating natural and environmental conditions of these parameters using distilled and tap water samples [132]. The results of this study and others [133] confirmed that laboratory results using ultrapure water samples are not representative of the real application in natural waters.

In studies done on surface water samples by Ireland et al. [134], it was concluded that inorganic-radical scavengers can have a major negative impact on the efficacy of the photocatalytic process, and the presence of organic matter in the water samples also degrades the *E. coli* inactivation kinetics.

Using a field-scale compound parabolic collector at the Swiss Federal Institute of Technology (EPFL), in Lausanne, natural water from the Lemman Lake was used to suspend *E. coli* in the presence of and irradiation under solar conditions [126]. From studies on the postirradiation period, the effective disinfection time (EDT) was defined as the time necessary to avoid bacterial regrowth after 24 h (or 48 h) in the dark after stopping phototreatment. It was suggested that the EDT necessary be used as an indicator of the impact of the solar photocatalytic process on bacteria instead of the UV dose required to achieve a certain level of disinfection.

8.3. Eutrophic Water Treatment

Another application of photocatalytic disinfection is in the treatment of eutrophic water. Control of algal blooms in eutrophic water is important because toxic cyanobacterial blooms in drinking water supplies may cause human health problems [137]. Copper-based algaecides can be used to control these blooms, however this method introduces secondary environmental problems [138].

Photocatalytic inactivation of three species of algae: *Anabaena*, *microcystis*, and *Melosira*, was studied using coated glass beads and UV-light irradiation [138]. Complete photocatalytic inactivation of *Anabaena*, *microcystis*, and *Melosira* was obtained in about 30 minutes, while the inactivation efficiency for *Melosira* was somewhat lower due to the inorganic siliceous wall surrounding the cells.

The floating-coated hollow glass beads were introduced into a mesocosm installed at the Nakdong River, Kimhae, Korea [138]. This mesocosm was a 25 m² and 2 m deep semipermeable membrane. The concentrations of chlorophyll-a were measured for one month, and it was shown that more than 50% of the chlorophyll-a concentration could be reduced using photocatalysts and natural solar radiation. A picture of the experimental mesocosm is depicted in Figure 2.

8.4. Groundwater Treatment

The ability of photocatalysis to break down and detoxify harmful organic chemicals has been exploited for groundwater treatment, as shown by engineering scale demonstrations using solar photocatalysis to remediate groundwater contaminated from leaking underground storage tanks [139].

The disinfecting abilities of photocatalytic processes for application to treating groundwater contaminated with microorganisms such as *F. Solani* [140] was also investigated and shown to be effective for the removal of such microorganisms. Natural well water containing the *F. Solani* species and solar illumination and employing CPCs was also explored as a process configuration for this application [141].

9. Conclusion

The photocatalytic technique is a versatile and efficient disinfection process capable of inactivating a wide range of harmful microorganisms in various media. It is a safe, nontoxic, and relatively inexpensive disinfection method whose adaptability allows it to be used for many purposes. Research in the field of photocatalytic disinfection is very diverse, covering a broad range of applications.

Particularly, the use of photocatalysis was shown to be effective for various air-cleaning applications to inactivate harmful airborne microbial pathogens, or to combat airborne bioterror threats, such as Anthrax. Photocatalytic thin films on

various substrates were also shown to have potential application for “self-disinfecting” surfaces and materials, which can be used for medical implants, “self-disinfecting” surgical tools and surfaces in laboratory and hospital settings, and equipment in the pharmaceutical and food industries. Photocatalytic food packaging was shown to be a potential way to reduce the risk of foodborne illnesses in cut lettuce and other packaged foods. In terms of plant protection, photocatalysis is being investigated for use in hydroponic agricultures as an alternative to harsh pesticides. For water treatment applications, photocatalytic disinfection has been studied and implemented for drinking water production using novel reactors and solar irradiation. Eutrophic waters containing algal blooms were also shown to be effectively treated using -coated hollow beads and solar irradiation.

The effectiveness of photocatalytic disinfection for inactivating microorganisms of concern for each of these applications was presented, highlighting key studies and research efforts conducted. While the performance of this technology is still to be optimized for the specific applications, based on the literature presented, it is abundantly evident that photocatalysis should be considered as a viable alternative to traditional disinfection methods in some cases.

In a move towards a more environmentally friendly world, traditional solutions to classic problems, such as the production of safe drinking water, must shift towards more sustainable alternatives. Photocatalytic disinfection is not only a replacement technology for traditional methods in traditional applications, but also a novel approach for solving other disinfection problems, such as the control of bioterror threats. In this sense, the strength of photocatalytic disinfection lies in its versatility for use in many different applications.

References

1. D. M. Blake, P.-C. Maness, Z. Huang, E. J. Wolfrum, J. Huang, and W. A. Jacoby, “Application of the photocatalytic chemistry of titanium dioxide to disinfection and the killing of cancer cells,” *Separation and Purification Methods*, vol. 28, no. 1, pp. 1–50, 1999. [View at Google Scholar](#)
2. K. Yogo and M. Ishikawa, “Recent progress in environmental catalytic technology,” *Catalysis Surveys from Japan*, vol. 4, no. 1, pp. 83–90, 2000. [View at Google Scholar](#)
3. D. Ljubic, “Solar photocatalysis—a possible step in drinking water treatment,” *Energy*, vol. 30, no. 10, pp. 1699–1710, 2005. [View at Publisher](#) · [View at Google Scholar](#)
4. H. J. Kool, C. F. Keijl, and J. Hrubec, *Water Chlorination: Chemistry, Environmental Impact and Health Effects*, Lewis, Chelsea, Mich, USA, 1985.
5. P. S. M. Dunlop, J. A. Byrne, N. Manga, and B. R. Eggers, “The photocatalytic removal of bacterial pollutants from drinking water,” *Journal of Photochemistry and Photobiology A*, vol. 148, no. 1–3, pp. 355–363, 2002. [View at Publisher](#) · [View at Google Scholar](#)
6. F. W. Pontis, Ed., *Water Quality and Treatment, A Handbook of Community Water Supplies*, Mc-Graw Hill, New York, NY, USA, 4th edition, 1990.
7. S. Regli, “Disinfection requirements to control for microbial contamination,” in *Regulating Drinking Water Quality*, C. E. Gilbert and E. J. Calabrese, Eds., Lewis, Mich, USA, 1992. [View at Google Scholar](#)
8. W. J. Masschelin, *Ultraviolet Light in Water and Wastewater Sanitation*, Lewis, Boca Raton, Fla, USA, 2002.
9. J. M. C. Robertson, P. K. J. Robertson, and L. A. Lawton, “A comparison of the effectiveness of TiO₂ photocatalysis and UVA photolysis for the destruction of three pathogenic micro-organisms,” *Journal of Photochemistry and Photobiology A*, vol. 175, no. 1, pp. 51–56, 2005. [View at Publisher](#) · [View at Google Scholar](#)
10. W.-J. Huang, G.-C. Fang, and C.-C. Wang, “The determination and fate of disinfection by-products from ozonation of polluted raw water,” *Science of the Total Environment*, vol. 345, no. 1–3, pp. 261–272, 2005. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
11. M. A. Fox, C. C. Chen, K. Park, and J. N. Younathan, in *Organic Transformations in Non-Homogeneous Media*, M. A. Fox, Ed., ACS Symposium Series, p. 278, 1985.
12. A. Fujishima, T. N. Rao, and D. A. Tryk, “Titanium dioxide photocatalysis,” *Journal of Photochemistry and Photobiology C*, vol. 1, no. 1, pp. 1–21, 2000. [View at Google Scholar](#)
13. A.-G. Rincón and C. Pulgarin, “Use of coaxial photocatalytic reactor (CAPHORE) in the TiO₂ photo-assisted treatment of mixed *E. coli* and *Bacillus* sp. and bacterial community present in wastewater,” *Catalysis Today*, vol. 101, no. 3–4, pp. 331–344, 2005. [View at Publisher](#) · [View at Google Scholar](#)
14. K. Sunada, T. Watanabe, and K. Hashimoto, “Studies on photokilling of bacteria on TiO₂ thin film,” *Journal of Photochemistry and Photobiology A*, vol. 156, no. 1–3, pp. 227–233, 2003. [View at Publisher](#) · [View at Google Scholar](#)
15. T. Matsunaga, R. Tomoda, T. Nakajima, and H. Wake, “Photoelectrochemical sterilization of microbial cells by semiconductor powders,” *FEMS Microbiology Letters*, vol. 29, no. 1–2, pp. 211–214, 1985. [View at Google Scholar](#)

16. C. McCullagh, J. M. C. Robertson, D. W. Bahnemann, and P. K. J. Robertson, "The application of TiO₂ photocatalysis for disinfection of water contaminated with pathogenic micro-organisms: a review," *Research on Chemical Intermediates*, vol. 33, no. 3-5, pp. 359–375, 2007. [View at Google Scholar](#)
17. D. Y. Goswami and D. M. Blake, "Cleaning up with sunshine," *Mechanical Engineering*, vol. 118, no. 8, pp. 56–59, 1996. [View at Google Scholar](#)
18. D. Y. Goswami, "A review of engineering developments of aqueous phase solar photocatalytic detoxification and disinfection processes," *Journal of Solar Energy Engineering, Transactions of the ASME*, vol. 119, no. 2, pp. 101–107, 1997. [View at Google Scholar](#)
19. M. Romero, J. Blanco, B. Sánchez et al., "Solar photocatalytic degradation of water and air pollutants: challenges and perspectives," *Solar Energy*, vol. 66, no. 2, pp. 169–182, 1999. [View at Google Scholar](#)
20. D. Y. Goswami, S. Vijayaraghavan, S. Lu, and G. Tamm, "New and emerging developments in solar energy," *Solar Energy*, vol. 76, no. 1-3, pp. 33–43, 2004. [View at Publisher](#) · [View at Google Scholar](#)
21. S. Malato, J. Blanco, D. C. Alarcón, M. I. Maldonado, P. Fernández-Ibáñez, and W. Gernjak, "Photocatalytic decontamination and disinfection of water with solar collectors," *Catalysis Today*, vol. 122, no. 1-2, pp. 137–149, 2007. [View at Publisher](#) · [View at Google Scholar](#)
22. S. S. Block and D. Y. Goswami, "Chemical enhanced sunlight for killing bacteria," in *Proceedings of the ASME International Solar Energy conference*, vol. 1, pp. 431–437, 1995.
23. R. Armon, N. Laot, N. Narkis, and I. Neeman, "Photocatalytic inactivation of different bacteria and bacteriophages in drinking water at different TiO₂ concentration with or without exposure to O₂," *Journal of Advanced Oxidation Technologies*, vol. 3, pp. 145–150, 1998. [View at Google Scholar](#)
24. A. T. Cooper, D. Y. Goswami, and S. S. Block, "Solar photochemical detoxification and disinfection for water treatment in tropical developing countries," *Journal of Advanced Oxidation Technologies*, vol. 3, no. 2, pp. 151–154, 1998. [View at Google Scholar](#)
25. M. Biguzzi and G. Shama, "Effect of titanium dioxide concentration on the survival of *Pseudomonas stutzeri* during irradiation with near ultraviolet light," *Letters in Applied Microbiology*, vol. 19, no. 6, pp. 458–460, 1994. [View at Google Scholar](#)
26. H. N. Pham, T. McDowell, and E. Wilkins, "Photocatalytically-mediated disinfection of water using TiO₂ as a catalyst and spore-forming *Bacillus pumilus* as a model," *Journal of Environmental Science and Health. Part A*, vol. 30, no. 3, pp. 627–636, 1995. [View at Google Scholar](#)
27. J. C. Sjogren and R. A. Sierka, "Inactivation of phage MS2 by iron-aided titanium dioxide photocatalysis," *Applied and Environmental Microbiology*, vol. 60, no. 1, pp. 344–347, 1994. [View at Google Scholar](#)
28. R. J. Watts, S. Kong, M. P. Orr, G. C. Miller, and B. E. Henry, "Photocatalytic inactivation of coliform bacteria and viruses in secondary wastewater effluent," *Water Research*, vol. 29, no. 1, pp. 95–100, 1995. [View at Publisher](#) · [View at Google Scholar](#)
29. H. Ryu, D. Gerrity, J. C. Crittenden, and M. Abbaszadeh, "Photocatalytic inactivation of *Cryptosporidium parvum* with TiO₂ and low-pressure ultraviolet irradiation," *Water Research*, vol. 42, no. 6-7, pp. 1523–1530, 2008. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
30. M. Sökmen, S. Değerli, and A. Aslan, "Photocatalytic disinfection of *Giardia intestinalis* and *Acanthamoeba castellanii* cysts in water," *Experimental Parasitology*, vol. 119, no. 1, pp. 44–48, 2008. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
31. S. M. Karvinen, "The effects of trace element doping on the optical properties and photocatalytic activity of nanostructured titanium dioxide," *Industrial and Engineering Chemistry Research*, vol. 42, no. 5, pp. 1035–1043, 2003. [View at Google Scholar](#)
32. A. Vohra, D. Y. Goswami, D. A. Deshpande, and S. S. Block, "Enhanced photocatalytic inactivation of bacterial spores on surfaces in air," *Journal of Industrial Microbiology and Biotechnology*, vol. 32, no. 3, pp. 364–370, 2005. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
33. E. V. Skorb, L. I. Antonouskaya, N. A. Belyasova, D. G. Shchukin, H. Möhwald, and D. V. Sviridov, "Antibacterial activity of thin-film photocatalysts based on metal-modified TiO₂ and TiO₂:In₂O₃ nanocomposite," *Applied Catalysis B*, vol. 84, no. 1-2, pp. 94–99, 2008. [View at Publisher](#) · [View at Google Scholar](#)
34. J. C. Yu, W. Ho, J. Yu, H. Yip, K. W. Po, and J. Zhao, "Efficient visible-light-induced photocatalytic disinfection on sulfur-doped nanocrystalline titania," *Environmental Science and Technology*, vol. 39, no. 4, pp. 1175–1179, 2005. [View at Publisher](#) · [View at Google Scholar](#)
35. G. Li, T. An, X. Nie et al., "Mutagenicity assessment of produced water during photoelectrocatalytic degradation," *Environmental Toxicology and Chemistry*, vol. 26, no. 3, pp. 416–423, 2007. [View at Publisher](#) · [View at Google Scholar](#)
36. T. P. T. Cushnie, P. K. J. Robertson, S. Officer, P. M. Pollard, C. McCullagh, and J. M. C. Robertson, "Variables to be considered when assessing the photocatalytic destruction of bacterial pathogens," *Chemosphere*, vol. 74, no. 10, pp. 1374–1378, 2009. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
37. Y.-S. Choi and B.-W. Kim, "Photocatalytic disinfection of *E. coli* in a UV/TiO₂-immobilised optical-fibre reactor," *Journal of Chemical Technology and Biotechnology*, vol. 75, no. 12, pp. 1145–1150, 2000. [View at Google Scholar](#)
38. M. Subrahmanyam, P. Boule, V. D. Kumar, D. N. Kumar, M. Sancelme, and A. Rachel, "Pumice stone supported titanium dioxide for removal of pathogen in drinking water and recalcitrant in wastewater," *Solar Energy*, vol. 82, no. 12, pp. 1099–1106, 2008. [View at Publisher](#) · [View at Google Scholar](#)
39. C. Guillard, T.-H. Bui, C. Felix, V. Moules, B. Lina, and P. Lejeune, "Microbiological disinfection of water and air by photocatalysis," *Comptes Rendus Chimie*, vol. 11, no. 1-2, pp. 107–113, 2008. [View at Publisher](#) · [View at Google Scholar](#)
40. D. T. Tompkins, W. A. Zeitner, B. J. Lawnicki, and M. A. Anderson, "Evaluation of photocatalysis for gas-phase air cleanin—part 1: process, technical, and sizing considerations," *ASHRAE Transactions*, vol. 111, no. 2, pp. 60–84, 2005. [View at Google Scholar](#)
41. D. F. Ollis, "Photocatalytic purification and remediation of contaminated air and water," *Comptes Rendus de l'Academie des Sciences IIC 3*, vol. 3, no. 6, pp. 405–411, 2000. [View at Google Scholar](#)
42. W. A. Jacoby, P. C. Maness, E. J. Wolfrum, D. M. Blake, and J. A. Fennell, "Mineralization of bacterial cell mass on a photocatalytic surface in air," *Environmental Science and Technology*, vol. 32, no. 17, pp. 2650–2653, 1998. [View at Publisher](#) · [View at Google Scholar](#)
43. D. Y. Goswami, D. M. Trivedi, and S. S. Block, "Photocatalytic disinfection of indoor air," *Journal of Solar Energy Engineering, Transactions of the ASME*, vol. 119, no. 1, pp. 92–96, 1997. [View at Google Scholar](#)
44. D. Y. Goswami, D. M. Trivedi, and S. S. Block, "Photocatalytic disinfection of indoor air," *Journal of Solar Energy Engineering, Transactions of the ASME*, vol. 119, no. 1, pp. 92–96, 1997. [View at Google Scholar](#)
45. T. K. Goswami, S. Hingorani, H. Griest, D. Y. Goswami, and S. S. Block, "Photocatalytic system to destroy bioaerosols in air," *Journal of Advanced Oxidation Technologies*, vol. 4, no. 2, pp. 185–188, 1999. [View at Google Scholar](#)
46. H. T. Griest, S. K. Hingorani, K. Kelly, and D. Y. Goswami, "Using scanning electron microscopy to visualize the photocatalytic mineralization of airborne microorganisms," in *Proceedings of the 9th International Conference on Indoor Air Quality and Climate, Processing of the Indoor Air*, pp. 712–717, Monterey, Calif, USA, 2002.
47. C. Lee, H. Choi, C. Lee, and H. Kim, "Photocatalytic properties of nano-structured TiO₂ plasma sprayed coating," *Surface and Coatings Technology*, vol. 173, no. 2-3, pp. 192–200, 2003. [View at Publisher](#) · [View at Google Scholar](#)
48. J.-H. Kau, D.-S. Sun, H.-H. Huang, M.-S. Wong, H.-C. Lin, and H.-H. Chang, "Role of visible light-activated photocatalyst on the reduction of anthrax spore-induced mortality in mice," *PLoS ONE*, vol. 4, no. 1, pp. 1–8, 2009. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
49. H. Knight, "Sars wars," *Engineer*, vol. 292, pp. 27–35, 2003. [View at Google Scholar](#)
50. D. Mitoraj, A. Jańczyk, M. Strus et al., "Visible light inactivation of bacteria and fungi by modified titanium dioxide," *Photochemical and Photobiological Sciences*, vol. 6, no. 6, pp. 642–648, 2007. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
51. A. Pal, S. O. Pehkonen, L. E. Yu, and M. B. Ray, "Photocatalytic inactivation of Gram-positive and Gram-negative bacteria using fluorescent light," *Journal of Photochemistry and Photobiology A*, vol. 186, no. 2-3, pp. 335–341, 2007. [View at Publisher](#) · [View at Google Scholar](#)
52. E. J. Wolfrum, J. Huang, D. M. Blake et al., "Photocatalytic oxidation of bacteria, bacterial and fungal spores, and model biofilm components to carbon dioxide on titanium dioxide-coated surfaces," *Environmental Science and Technology*, vol. 36, no. 15, pp. 3412–3419, 2002. [View at Publisher](#) · [View at Google Scholar](#)
53. J. Kiwi and V. Nadtochenko, "New evidence for TiO₂ photocatalysis during bilayer lipid peroxidation," *Journal of Physical Chemistry B*, vol. 108, no. 45, pp. 17675–17684, 2004. [View at Publisher](#) · [View at Google Scholar](#)
54. R. Basca, J. Kiwi, T. Ohno, P. Albers, and V. Nadtochenko, "Preparation, testing and characterization of doped TiO₂ able to transform biomolecules under visible light irradiation by peroxidation/oxidation," *Journal Physical Chemistry B*, vol. 109, pp. 5994–6003, 2005. [View at Google Scholar](#)
55. J. Kiwi and V. Nadtochenko, "Evidence for the mechanism of photocatalytic degradation of the bacterial wall membrane at the TiO₂ interface by ATR-FTIR and laser kinetic spectroscopy," *Langmuir*, vol. 21, no. 10, pp. 4631–4641, 2005. [View at Publisher](#) · [View at Google Scholar](#)

56. V. A. Nadochenko, A. G. Rincon, S. E. Stanca, and J. Kiwi, "Dynamics of E. coli membrane cell peroxidation during TiO₂ photocatalysis studied by ATR-FTIR spectroscopy and AFM microscopy," *Journal of Photochemistry and Photobiology A*, vol. 169, no. 2, pp. 131–137, 2005. [View at Publisher](#) · [View at Google Scholar](#)
57. V. Nadochenko, C. Pulgarin, P. Bowen, and J. Kiwi, "Laser spectroscopy of the interaction of bacterial wall membranes and E. coli with TiO₂," *Journal of Photochemistry and Photobiology A*, vol. 181, pp. 401–404, 2006. [View at Google Scholar](#)
58. M. P. Paschoalino and W. F. Jardim, "Indoor air disinfection using a polyester supported TiO₂ photo-reactor," *Indoor Air*, vol. 18, no. 6, pp. 473–479, 2008. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
59. V. Krishna, S. Pumprug, S.-H. Lee et al., "Photocatalytic disinfection with titanium dioxide coated multi-wall carbon nanotubes," *Process Safety and Environmental Protection*, vol. 83, no. 4 B, pp. 393–397, 2005. [View at Publisher](#) · [View at Google Scholar](#)
60. S. A. Grinshpun, A. Adhikari, T. Honda et al., "Control of aerosol contaminants in indoor air: combining the particle concentration reduction with microbial inactivation," *Environmental Science and Technology*, vol. 41, no. 2, pp. 606–612, 2007. [View at Publisher](#) · [View at Google Scholar](#)
61. A. Pal, X. Mint, L. E. Yu, S. O. Pehkonen, and M. B. Ray, "Photocatalytic inactivation of bioaerosols by TiO₂ coated membrane," *International Journal of Chemical Reactor Engineering*, vol. 3, p. A45, 2005. [View at Google Scholar](#)
62. T. Yuranova, A. G. Rincon, A. Bozzi et al., "Antibacterial textiles prepared by RF-plasma and vacuum-UV mediated deposition of silver," *Journal of Photochemistry and Photobiology A*, vol. 161, no. 1, pp. 27–34, 2003. [View at Publisher](#) · [View at Google Scholar](#)
63. T. Yuranova, A. G. Rincon, C. Pulgarin, D. Laub, N. Xantopoulos, and H.-J. Mathieu, "Bactericide cotton textiles active in E. coli abatement prepared under mild preparation conditions," *Journal of Photochemistry and Photobiology A*, vol. 181, pp. 363–369, 2006. [View at Google Scholar](#)
64. M. I. Mejia, G. Restrepo, J. M. Marin, R. Sanjines, C. Pulgarin, and E. Mielczarski, "Magnetron-sputtered Ag surfaces. New evidence for the nature of the Ag ions intervening in bacterial inactivation," *JACS Applied Materials and Interfaces*, vol. 2, pp. 230–235, 2010. [View at Google Scholar](#)
65. M. Paschoalino, N. C. Guedes, W. Jardim, E. Mielczarski, K. Mielczarski, and P. Bowen, "Photo-assisted inactivation of E. coli by high surface area CuO under light irradiation (>360 nm)," *Journal of Photochemistry and Photobiology A*, vol. 199, pp. 105–111, 2008. [View at Google Scholar](#)
66. A. Moncayo-Lasso, R. A. Torres-Palma, J. Kiwi, N. Benítez, and C. Pulgarin, "Bacterial inactivation and organic oxidation via immobilized photo-Fenton reagent on structured silica surfaces," *Applied Catalysis B*, vol. 84, no. 3–4, pp. 577–583, 2008. [View at Publisher](#) · [View at Google Scholar](#)
67. F. Chen, X. Yang, and Q. Wu, "Antifungal capability of TiO₂ coated film on moist wood," *Building and Environment*, vol. 44, no. 5, pp. 1088–1093, 2009. [View at Publisher](#) · [View at Google Scholar](#)
68. P. Kern, P. Schwaller, and J. Michler, "Electrolytic deposition of titania films as interference coatings on biomedical implants: microstructure, chemistry and nano-mechanical properties," *Thin Solid Films*, vol. 494, no. 1–2, pp. 279–286, 2006. [View at Publisher](#) · [View at Google Scholar](#)
69. P. Evans and D. W. Sheel, "Photoactive and antibacterial TiO₂ thin films on stainless steel," *Surface and Coatings Technology*, vol. 201, no. 22–23, pp. 9319–9324, 2007. [View at Publisher](#) · [View at Google Scholar](#)
70. K. Shiraishi, H. Koseki, T. Tsurumoto et al., "Antibacterial metal implant with a TiO₂-conferred photocatalytic bactericidal effect against *Staphylococcus aureus*," *Surface and Interface Analysis*, vol. 41, no. 1, pp. 17–22, 2009. [View at Publisher](#) · [View at Google Scholar](#)
71. Y. Kubota, T. Shuin, C. Kawasaki et al., "Photokilling of T-24 human bladder cancer cells with titanium dioxide," *British Journal of Cancer*, vol. 70, no. 6, pp. 1107–1111, 1994. [View at Google Scholar](#)
72. H. Irie, K. Sunada, and K. Hashimoto, "Recent developments in TiO₂ photocatalysis: novel applications to interior ecology materials and energy saving systems," *Electrochemistry*, vol. 72, no. 12, pp. 807–812, 2004. [View at Google Scholar](#)
73. S.-H. Lee, S. Pumprug, B. Moudgil, and W. Sigmund, "Inactivation of bacterial endospores by photocatalytic nanocomposites," *Colloids and Surfaces B*, vol. 40, no. 2, pp. 93–98, 2005. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
74. K. P. Kühn, I. F. Chaberny, K. Massholder et al., "Disinfection of surfaces by photocatalytic oxidation with titanium dioxide and UVA light," *Chemosphere*, vol. 53, no. 1, pp. 71–77, 2003. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
75. Y. Kikuchi, K. Sunada, T. Iyoda, K. Hashimoto, and A. Fujishima, "Photocatalytic bactericidal effect of TiO₂ thin films: dynamic view of the active oxygen species responsible for the effect," *Journal of Photochemistry and Photobiology A*, vol. 106, no. 1–3, pp. 51–56, 1997. [View at Google Scholar](#)
76. P. Evans, T. English, D. Hammond, M. E. Pemble, and D. W. Sheel, "The role of SiO₂ barrier layers in determining the structure and photocatalytic activity of TiO₂ films deposited on stainless steel," *Applied Catalysis A*, vol. 321, no. 2, pp. 140–146, 2007. [View at Publisher](#) · [View at Google Scholar](#)
77. L. Caballero, K. A. Whitehead, N. S. Allen, and J. Verran, "Inactivation of *Escherichia coli* on immobilized TiO₂ using fluorescent light," *Journal of Photochemistry and Photobiology A*, vol. 202, no. 2–3, pp. 92–98, 2009. [View at Publisher](#) · [View at Google Scholar](#)
78. J. C. Yu, W. Ho, J. Lin, H. Yip, and P. K. Wong, "Photocatalytic activity, antibacterial effect, and photoinduced hydrophilicity of TiO₂ films coated on a stainless steel substrate," *Environmental Science and Technology*, vol. 37, no. 10, pp. 2296–2301, 2003. [View at Publisher](#) · [View at Google Scholar](#)
79. K. Sunada, T. Watanabe, and K. Hashimoto, "Bactericidal activity of copper-deposited TiO₂ thin film under weak UV light illumination," *Environmental Science and Technology*, vol. 37, no. 20, pp. 4785–4789, 2003. [View at Publisher](#) · [View at Google Scholar](#)
80. M.-S. Wong, W.-C. Chu, D.-S. Sun et al., "Visible-light-induced bactericidal activity of a nitrogen-doped titanium photocatalyst against human pathogens," *Applied and Environmental Microbiology*, vol. 72, no. 9, pp. 6111–6116, 2006. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
81. J. A. Rengifo-Herrera, E. Mielczarski, J. Mielczarski, N. C. Castillo, J. Kiwi, and C. Pulgarin, "Escherichia coli inactivation by N, S co-doped commercial TiO₂ powders under UV and visible light," *Applied Catalysis B*, vol. 84, no. 3–4, pp. 448–456, 2008. [View at Publisher](#) · [View at Google Scholar](#)
82. J. A. Rengifo-Herrera, K. Pierzchala, A. Sienkiewicz, L. Forró, J. Kiwi, and C. Pulgarin, "Abatement of organics and *Escherichia coli* by N, S co-doped TiO₂ under UV and visible light. Implications of the formation of singlet oxygen (¹O₂) under visible light," *Applied Catalysis B*, vol. 88, no. 3–4, pp. 398–406, 2009. [View at Publisher](#) · [View at Google Scholar](#)
83. J. A. Rengifo-Herrera, J. Kiwi, and C. Pulgarin, "N, S co-doped and N-doped Degussa P-25 powders with visible light response prepared by mechanical mixing of thiourea and urea. Reactivity towards E. coli inactivation and phenol oxidation," *Journal of Photochemistry and Photobiology A*, vol. 205, no. 2–3, pp. 109–115, 2009. [View at Publisher](#) · [View at Google Scholar](#)
84. J. A. Rengifo-Herrera, A. Sienkiewicz, L. Forró, J. Kiwi, J. E. Moser, and C. Pulgarin, "New evidence for the nature of the N, S, co-doped TiO₂ sited under visible light leading to E. coli inactivation. Catalyst characterization," *Journal of Physical Chemistry*, vol. 114, pp. 2717–2723, 2010. [View at Google Scholar](#)
85. B. A. Walther and P. W. Ewald, "Pathogen survival in the external environment and the evolution of virulence," *Biological Reviews of the Cambridge Philosophical Society*, vol. 79, no. 4, pp. 849–869, 2004. [View at Publisher](#) · [View at Google Scholar](#)
86. K.-T. Chen, P.-Y. Chen, R.-B. Tang et al., "Sentinel hospital surveillance for rotavirus diarrhea in Taiwan, 2001–2003," *Journal of Infectious Diseases*, vol. 192, no. 1, pp. S44–S48, 2005. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
87. N. Laot, N. Narkis, I. Neeman, and R. Armon, "TiO₂ photocatalytic inactivation of selected microorganisms under various conditions: sunlight, intermittent and variable irradiation intensity, CdS supplementation and entrapment of TiO₂ into sol-gel," *Journal of Advanced Oxidation Technologies*, vol. 4, pp. 97–102, 1999. [View at Google Scholar](#)
88. Y. W. Cheng, R. C. Y. Chan, and P. K. Wong, "Disinfection of *Legionella pneumophila* by photocatalytic oxidation," *Water Research*, vol. 41, no. 4, pp. 842–852, 2007. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
89. Centers for Disease Control and Prevention, Hospital Control Practices Advisory Committee, "Guidelines for prevention of nosocomial pneumonia," *CDC's Morbidity and Mortality Weekly Reporter*, vol. 46, pp. 1–79, 1997. [View at Google Scholar](#)
90. C. Chawengkijwanich and Y. Hayata, "Development of TiO₂ powder-coated food packaging film and its ability to inactivate *Escherichia coli* in vitro and in actual tests," *International Journal of Food Microbiology*, vol. 123, no. 3, pp. 288–292, 2008. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
91. A. K. Benabbou, Z. Derriche, C. Felix, P. Lejeune, and C. Guillard, "Photocatalytic inactivation of *Escherichia coli*. Effect of concentration of TiO₂ and microorganism, nature, and intensity of UV irradiation," *Applied Catalysis B*, vol. 76, no. 3–4, pp. 257–263, 2007. [View at Publisher](#) · [View at Google Scholar](#)

92. Y. Liu, J. Li, X. Qiu, and C. Burda, "Bactericidal activity of nitrogen-doped metal oxide nanocatalysts and the influence of bacterial extracellular polymeric substances (EPS)," *Journal of Photochemistry and Photobiology A*, vol. 190, no. 1, pp. 94–100, 2007. [View at Publisher](#) · [View at Google Scholar](#)
93. H. Matsubara, M. Takada, and S. Koyama, "Research on application of photoactive TiO₂ to paper," *Kinoshiki Kenkyu Kaishi*, vol. 34, pp. 36–39, 1996. [View at Google Scholar](#)
94. J. Blanco, S. Malato, P. Fernández-Ibáñez, D. Alarcón, W. Gernjak, and M. I. Maldonado, "Review of feasible solar energy applications to water processes," *Renewable and Sustainable Energy Reviews*, vol. 13, no. 6-7, pp. 1437–1445, 2009. [View at Publisher](#) · [View at Google Scholar](#)
95. K. S. Yao, D. Y. Wang, W. Y. Ho, J. J. Yan, and K. C. Tzeng, "Photocatalytic bactericidal effect of TiO₂ thin film on plant pathogens," *Surface and Coatings Technology*, vol. 201, no. 15, pp. 6886–6888, 2007. [View at Publisher](#) · [View at Google Scholar](#)
96. K. S. Yao, D. Y. Wang, C. Y. Chang et al., "Photocatalytic disinfection of phytopathogenic bacteria by dye-sensitized TiO₂ thin film activated by visible light," *Surface and Coatings Technology*, vol. 202, no. 4-7, pp. 1329–1332, 2007. [View at Publisher](#) · [View at Google Scholar](#)
97. C. Sichel, M. de Cara, J. Tello, J. Blanco, and P. Fernández-Ibáñez, "Solar photocatalytic disinfection of agricultural pathogenic fungi: *Fusarium* species," *Applied Catalysis B*, vol. 74, no. 1-2, pp. 152–160, 2007. [View at Publisher](#) · [View at Google Scholar](#)
98. D. Sawada, M. Ohmasa, M. Fukuda et al., "Disinfection of some pathogens of mushroom cultivation by photocatalytic treatment," *Mycoscience*, vol. 46, no. 1, pp. 54–60, 2005. [View at Publisher](#) · [View at Google Scholar](#)
99. R. Dillert, S. Vollmer, M. Schöber et al., "Pilot plant studies on the photocatalytic oxidation of a pretreated industrial wastewater," *GWF Wasser Abwasser*, vol. 140, no. 4, pp. 293–297, 1999. [View at Google Scholar](#)
100. R. Dillert, S. Vollmer, E. Gross et al., "Solar-catalytic treatment of an industrial wastewater," *Zeitschrift für Physikalische Chemie*, vol. 213, no. 2, pp. 141–147, 1999. [View at Google Scholar](#)
101. R. Dillert, S. Vollmer, M. Schöber et al., "Photokatalytische Behandlung eines Industriebwassers im Stegdoppelplattenreaktor," *Chemie Ingenieur Technik*, vol. 71, pp. 396–399, 1999. [View at Google Scholar](#)
102. D. Bahnemann, "Photocatalytic water treatment: solar energy applications," *Solar Energy*, vol. 77, no. 5, pp. 445–459, 2004. [View at Publisher](#) · [View at Google Scholar](#)
103. J. Blanco and S. Malato, "Solar photocatalytic mineralization of real hazardous waste water at pre-industrial level," in *Proceedings of the ASME/JSME/SEES International Solar Energy Conference*, D. E. Klett, R. E. Hogan, and T. Tanaka, Eds., pp. 103–109, San Francisco, Calif, USA, 1994.
104. M. Anhegen, D. Y. Goswami, and G. Svedberg, "Photocatalytic treatment of wastewater from 5-fluoracil manufacturing," in *Proceedings of the ASME/JSME/SEES International Solar Energy Conference*, Maui, Hawaii, 1995.
105. A. H. Zaidi, D. Y. Goswami, and A. C. Wilkie, "Solar photocatalytic post-treatment of anaerobically digested distillery effluent," in *Proceedings of the American Solar Energy Society Annual Conference*, pp. 51–56, Minneapolis, Minn, USA, 1995.
106. C. S. Turchi, L. Edmunson, and D. F. Ollis, "Application of heterogeneous photocatalysis for the destruction of organic contaminants from a paper mill alkali extraction process," in *Proceedings of the TAPPI 5th International Symposium on Wood and Pulping Chemistry*, Raleigh, NC, USA, 1989.
107. O. Seven, B. Dindar, S. Aydemir, D. Metin, M. A. Ozinel, and S. Icli, "Solar photocatalytic disinfection of a group of bacteria and fungi aqueous suspensions with TiO₂, ZnO and Sahara desert dust," *Journal of Photochemistry and Photobiology A*, vol. 165, no. 1–3, pp. 103–107, 2004. [View at Publisher](#) · [View at Google Scholar](#)
108. M. Otaki, T. Hirata, and S. Ohgaki, "Aqueous microorganisms inactivation by photocatalytic reaction," *Water Science and Technology*, vol. 42, no. 3-4, pp. 103–108, 2000. [View at Google Scholar](#)
109. T. Kato, T. Shibata, H. Tohma, M. Tamura, and O. Miki, "Degradation of norovirus in sewage treatment water by photocatalytic ultraviolet disinfection," *Nippon Steel Technical Report*, pp. 41–44, 92. [View at Google Scholar](#)
110. R. Dillert, U. Siemon, and D. Bahnemann, "Photocatalytic disinfection of municipal wastewater," *Chemical Engineering and Technology*, vol. 21, no. 4, pp. 356–358, 1998. [View at Google Scholar](#)
111. J. A. Herrera Melián, J. M. Doña Rodríguez, A. Viera Suárez et al., "The photocatalytic disinfection of urban waste waters," *Chemosphere*, vol. 41, no. 3, pp. 323–327, 2000. [View at Publisher](#) · [View at Google Scholar](#)
112. A.-G. Rincón and C. Pulgarín, "Bactericidal action of illuminated TiO₂ on pure *Escherichia coli* and natural bacterial consortia: post-irradiation events in the dark and assessment of the effective disinfection time," *Applied Catalysis B*, vol. 49, no. 2, pp. 99–112, 2004. [View at Publisher](#) · [View at Google Scholar](#)
113. A. G. Rincón and C. Pulgarín, "Photocatalytic inactivation of *E. coli*: effect of (continuous-intermittent) light intensity and of (suspended-fixed) TiO₂ concentration," *Applied Catalysis B*, vol. 44, no. 3, pp. 263–284, 2003. [View at Publisher](#) · [View at Google Scholar](#)
114. Y. Li, M. Ma, X. Wang, and X. Wang, "Inactivated properties of activated carbon-supported TiO₂ nanoparticles for bacteria and kinetic study," *Journal of Environmental Sciences*, vol. 20, no. 12, pp. 1527–1533, 2008. [View at Publisher](#) · [View at Google Scholar](#)
115. H. Choi, A. C. Sofranko, and D. D. Dionysiou, "Nanocrystalline TiO₂ photocatalytic membranes with a hierarchical mesoporous multilayer structure: synthesis, characterization, and multifunction," *Advanced Functional Materials*, vol. 16, no. 8, pp. 1067–1074, 2006. [View at Publisher](#) · [View at Google Scholar](#)
116. H. Choi, E. Stathatos, and D. D. Dionysiou, "Photocatalytic TiO₂ films and membranes for the development of efficient wastewater treatment and reuse systems," *Desalination*, vol. 202, no. 1-3, pp. 199–206, 2007. [View at Publisher](#) · [View at Google Scholar](#)
117. Y. Liu, J. Li, X. Qiu, and C. Burda, "Novel TiO₂ nanocatalysts for wastewater purification: tapping energy from the sun," *Water Science and Technology*, vol. 54, no. 8, pp. 47–54, 2006. [View at Publisher](#) · [View at Google Scholar](#)
118. P. H. Gleick, *World's Water 2004-2005*, Island Press, Washington, DC, USA, 2004.
119. L. Villen, F. Manjon, D. García-Fresnadillo, and G. Orellana, "Solar water disinfection by photocatalytic singlet oxygen production in heterogenous medium," *Applied Catalysis B*, vol. 69, pp. 1–9, 2006. [View at Google Scholar](#)
120. I. Najm and R. R. Trussel, "New and emerging drinking water treatment technologies," in *Identifying Future Drinking Water Contaminants*, p. 220, National Academy, Washington, DC, USA, 1999. [View at Google Scholar](#)
121. M. Boyle, C. Sichel, P. Fernández-Ibáñez et al., "Bactericidal effect of solar water disinfection under real sunlight conditions," *Applied and Environmental Microbiology*, vol. 74, no. 10, pp. 2997–3001, 2008. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
122. E. Ubomba-Jaswa, C. Navtoft, I. Polo-López, P. Fernández-Ibáñez, and K. G. McGuigan, "Solar disinfection of drinking water (SODIS): an investigation of the effect of UVA dose on inactivation efficiency," *Photochemistry and Photobiological Sciences*, vol. 8, no. 5, pp. 587–595, 2009. [View at Google Scholar](#)
123. H. Gómez-Couso, M. Fontán-Saínz, C. Sichel, P. Fernández-Ibáñez, and E. Ares-Mazás, "Solar disinfection of turbid waters experimentally contaminated with *Cryptosporidium parvum* oocysts under real field conditions," *Tropical Medicine and International Health*, vol. 14, no. 6, pp. 1–9, 2009. [View at Google Scholar](#)
124. E. Ubomba-Jaswa, P. Fernández-Ibáñez, C. Navtoft, M. Inmaculada Polo-López, and K. G. McGuigan, "Investigating the microbial inactivation efficiency of a 25 L batch solar disinfection (SODIS) reactor enhanced with a compound parabolic collector (CPC) for household use," *Journal of Chemical Technology and Biotechnology*, vol. 85, no. 8, pp. 1028–1037, 2010. [View at Publisher](#) · [View at Google Scholar](#)
125. O. A. McLoughlin, P. Fernández-Ibáñez, W. Gernjak, S. Malato Rodríguez, and L. W. Gill, "Photocatalytic disinfection of water using low cost compound parabolic collectors," *Solar Energy*, vol. 77, no. 5, pp. 625–633, 2004. [View at Publisher](#) · [View at Google Scholar](#)
126. A.-G. Rincón and C. Pulgarín, "Field solar *E. coli* inactivation in the absence and presence of TiO₂: is UV solar dose an appropriate parameter for standardization of water solar disinfection?" *Solar Energy*, vol. 77, no. 5, pp. 635–648, 2004. [View at Publisher](#) · [View at Google Scholar](#)
127. C. Navtoft, P. Araujo, M. I. Litter et al., "Field tests of the solar water detoxification SOLWATER reactor in Los Pereyra, Tucumán, Argentina," *Journal of Solar Energy Engineering, Transactions of the ASME*, vol. 129, no. 1, pp. 127–134, 2007. [View at Publisher](#) · [View at Google Scholar](#)
128. E. F. Duffy, F. Al Touati, S. C. Kehoe et al., "A novel TiO₂-assisted solar photocatalytic batch-process disinfection reactor for the treatment of biological and chemical contaminants in domestic drinking water in developing countries," *Solar Energy*, vol. 77, no. 5, pp. 649–655, 2004. [View at Publisher](#) · [View at Google Scholar](#)

129. F. Méndez-Hermida, E. Ares-Mazás, K. G. McGuigan, M. Boyle, C. Sichel, and P. Fernández-Ibáñez, "Disinfection of drinking water contaminated with *Cryptosporidium parvum* oocysts under natural sunlight and using the photocatalyst TiO_2 ," *Journal of Photochemistry and Photobiology B*, vol. 88, no. 2-3, pp. 105–111, 2007. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
130. H. Gómez-Couso, M. Fontán-Sainz, J. Fernández-Alonso, and E. Ares-Mazás, "Excystation of *Cryptosporidium parvum* at temperatures that are reached during solar water disinfection," *Parasitology*, vol. 136, no. 4, pp. 393–399, 2009. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
131. K. G. McGuigan, F. Méndez-Hermida, J. A. Castro-Hermida et al., "Batch solar disinfection inactivates oocysts of *Cryptosporidium parvum* and cysts of *Giardia muris* in drinking water," *Journal of Applied Microbiology*, vol. 101, no. 2, pp. 453–463, 2006. [View at Publisher](#) · [View at Google Scholar](#) · [View at PubMed](#)
132. A.-G. Rincón and C. Pulgarin, "Effect of pH, inorganic ions, organic matter and H_2O_2 on *E. coli* K12 photocatalytic inactivation by TiO_2 : implications in solar water disinfection," *Applied Catalysis B*, vol. 51, no. 4, pp. 283–302, 2004. [View at Publisher](#) · [View at Google Scholar](#)
133. J. Marugán, R. van Grieken, C. Sordo, and C. Cruz, "Kinetics of the photocatalytic disinfection of *Escherichia coli* suspensions," *Applied Catalysis B*, vol. 82, no. 1-2, pp. 27–36, 2008. [View at Publisher](#) · [View at Google Scholar](#)
134. J. C. Ireland, P. Klostermann, E. W. Rice, and R. M. Clark, "Inactivation of *Escherichia coli* by titanium dioxide photocatalytic oxidation," *Applied and Environmental Microbiology*, vol. 59, no. 5, pp. 1668–1670, 1993. [View at Google Scholar](#)
135. J. Wist, J. Sanabria, C. Dierolf, W. Torres, and C. Pulgarin, "Evaluation of photocatalytic disinfection of crude water for drinking-water production," *Journal of Photochemistry and Photobiology A*, vol. 147, no. 3, pp. 241–246, 2002. [View at Publisher](#) · [View at Google Scholar](#)
136. C. A. Murray, E. H. Goslan, and S. A. Parsons, " TiO_2 /UV: single stage drinking water treatment for NOM removal?" *Journal of Environmental Engineering and Science*, vol. 6, no. 3, pp. 311–317, 2007. [View at Publisher](#) · [View at Google Scholar](#)
137. S.-C. Kim and D.-K. Lee, "Inactivation of algal blooms in eutrophic water of drinking water supplies with the photocatalysis of TiO_2 thin film on hollow glass beads," *Water Science and Technology*, vol. 52, no. 9, pp. 145–152, 2005. [View at Google Scholar](#)
138. A. J. Feitz, T. D. Waite, G. J. Jones, B. H. Boyden, and P. T. Orr, "Photocatalytic degradation of the blue-green algal toxin Microcystin-LR in a natural organic-aqueous matrix," *Environmental Science and Technology*, vol. 33, no. 2, pp. 243–249, 1999. [View at Google Scholar](#)
139. D. Y. Goswami, J. Klausner, G. D. Mathur et al., "Solar photocatalytic treatment of groundwater at Tyndall AFB, field test results," in *Proceedings of the American Solar Energy Society Annual Conference*, Washington, DC, USA, 1993.
140. P. Fernández-Ibáñez, C. Sichel, M. I. Polo-López, M. de Cara-García, and J. C. Tello, "Photocatalytic disinfection of natural well water contaminated by *Fusarium solani* using TiO_2 slurry in solar CPC photo-reactors," *Catalysis Today*, vol. 144, no. 1-2, pp. 62–68, 2009. [View at Publisher](#) · [View at Google Scholar](#)
141. M. I. Polo-López, P. Fernández-Ibáñez, I. García-Fernández, I. Oller, I. Salgado-Tránsito, and C. Sichel, "Resistance of *Fusarium* sp spores to solar TiO_2 photocatalysis: influence of spore type and water (scaling-up results)," *Journal of Chemical Technology and Biotechnology*, vol. 85, pp. 1038–1048, 2010. [View at Google Scholar](#)